



TECHNICAL DATA SHEET

Order reference	SPC200-E
Article number	813737

Date	4-11-11	Replaces	6-12-06	No. Pages	1
-------------	---------	-----------------	---------	------------------	---

Product Description:

Style	Pads; perforated on centerline for dividing in half for smaller applications
Item Size (each)	41cm x 51cm
Color	White
Composition	100% Polypropylene
Structure	Nonwoven mat of randomly oriented Micro-fibers [4-10 micron diameters]
Technology	Meltblown, 1-ply
Absorbency	Hydrophobic + Oleophilic
Bonding	Mechanical entanglement, Dimpled (no Spunbound)

Intended Application	Chemical Resistant Sorbent for Oil & Solvent Base Liquids
-----------------------------	---

Absorbency Capacity	166 l per bale (saturated; medium viscosity-18x)
----------------------------	--

Packaging Description:

Package configuration	1 Case	Pkg. Weight	9.6 kg (7.9 kg)
Items per Package	200 Pads/ Case	Pkg. Dimensions	43cm x 52cm x 55cm H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002	G/M2	190	19
Caliper	SPCTM-020	mm	4.0	0.4
Absorbency** (med.visc.)	SPCTM-004B	gL/gS	18	2
Tensile Strength	SPCTM-007	daN	6.0	0.6
Color	Visual	-----	White	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

This product complies with the specifications for Oil Binding Agents for type I, II, III SF according to MPA and German Hygiene health institute.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.